



asota

ASOTA Ges.m.b.H.
Schachermayerstr. 22
A-4020 Linz / Austria

2007

EN 14889-2

Polymer fibres for other purpose in concrete and mortar

Polymer: Polypropylene

Class I

Length: 12 mm

Diameter: 32 μm (7 dtex)

Cross section: round

Tenacity: > 315 N/mm² (> 35 cN/tex)

Consistency (dosage 0.9 kg fibres /m³ concrete [C25/30]):

Slump: - 3.2 cm

Compaction: + 0.09

Vebe time: + 7 sec.

(all above data's are mean values)